

# ケルビンプローブ顕微鏡による セラミックコンデンサ電極間の2次元電位プロファイル計測

○ T. Hiasa<sup>1,2</sup>, K. Kimura<sup>1,2</sup>, H. Onishi<sup>1,2</sup>, R. Kokawa<sup>1,5</sup>, M. Ohta<sup>1,5</sup>, K. Watanabe<sup>1,5</sup>,  
N. Oyabu<sup>1,3</sup>, K. Kobayashi<sup>1,4</sup>, H. Yamada<sup>1,3</sup>, T. Inao<sup>6</sup>

1 JST先端計測分析技術・機器開発事業, 2 神大理化, 3 京大電子工, 4 京大ICC, 5 島津製作所, 6 村田製作所

課題: セラミックコンデンサ内の2次元電位プロファイルから誘電体の均質性、界面での電位勾配(電界集中など)を調べることにより、長期使用時に発生する不良動作を未然に防ぐ。

実験結果: セラミックコンデンサ断面において、電圧印加時に2次元電位プロファイルを測定することができた。  
測定面においては急峻な電位勾配は存在しなかった。今後、不良品、良品の比較を行う。

## Principle of Kelvin-probe Force Microscopy (KPFM)

- KFM is based on Electrostatic Force (ESF) Detection.
- KFM signal is Effected by Band-Bending and Surface States.


$$U = \frac{1}{2} CV^2 \quad V(r): \text{potential distribution inside a device}$$

$$F = \frac{\partial U}{\partial z} = \frac{1}{2} \frac{\partial C}{\partial z} V^2 \quad \square \quad V = V_{dc} + V_{ac} \cos \omega t$$


$$F = \frac{1}{2} \frac{\partial C}{\partial z} [(V_{dc} + V(r))^2 + 2(V_{dc} + V(r))V_{ac} \cos \omega t + V_{ac}^2 \cos^2 \omega t]$$

$$F = \frac{1}{4} \frac{\partial C}{\partial z} (V_{ac}^2 + V_{ac}^2 \cos 2\omega t) \quad \square \quad V_{dc} = -V(r)$$

## Sample preparation



## Setup for KPFM




Applied voltage between two electrodes A, B

$$V_B = 3.0 \text{ V}$$

2D - Potential distribution

$$V_{ac} = 2.0 \text{ Vpp}$$




Applied voltage between two electrodes A, B

$$V_B = -3.0 \text{ V}$$

2D - Potential distribution

$$V_{ac} = 2.0 \text{ Vpp}$$



## Topographic Image

20  $\mu\text{m}$



KPFM imaging area  $44 \mu\text{m} \times 44 \mu\text{m}$

2D electric potential distribution was successfully measured by KPFM on cross-sectional ceramic condenser.

Abrupt potential drop was not observed on the cross-sectional plan.

As a future work, we have a plan to measure 2D potential on rejected pieces.